

## PATENT COOPERATION TREATY

PCT

NOTIFICATION OF THE RECORDING  
OF A CHANGE(PCT Rule 92bis.1 and  
Administrative Instructions, Section 422)

From the INTERNATIONAL BUREAU

To:

VAN REET, Joseph  
Gevers & Vander Haeghen  
Rue de Livourne 7  
B-1060 Brussels  
BELGIQUE

Date of mailing (day/month/year)

03 août 2001 (03.08.01)

Applicant's or agent's file reference

DPPC 126.595

## IMPORTANT NOTIFICATION

International application No.

PCT/BE99/00128

International filing date (day/month/year)

15 octobre 1999 (15.10.99)

1. The following indications appeared on record concerning:



the applicant



the inventor

RECEIVED

the agent



the common representative

Name and Address

LIMPAC MOULDINGS LTD.  
3180 Park Square  
Birmingham B37 7YN  
United Kingdom

NOV 21 2001

TC 1700

State of Nationality

GB

State of Residence

GB

Telephone No.

Facsimile No.

Teleprinter No.

2. The International Bureau hereby notifies the applicant that the following change has been recorded concerning:



the person



the name



the address



the nationality



the residence

Name and Address

RECTICEL  
Plejadelaan 15  
B-1200 Brussels  
Belgium

State of Nationality

BE

State of Residence

BE

Telephone No.

Facsimile No.

Teleprinter No.

3. Further observations, if necessary:

Due to an assignment RECTICEL is now applicant for all designated States except EP & US.  
LIMPAC MOULDINGS LTD. remains applicant for EP only.

4. A copy of this notification has been sent to:



the receiving Office



the designated Offices concerned



the International Searching Authority



the elected Offices concerned



the International Preliminary Examining Authority



other:

The International Bureau of WIPO  
34, chemin des Colombettes  
1211 Geneva 20, Switzerland

Authorized officer

S. Buttay

Facsimile No.: (41-22) 740.14.35

Telephone No.: (41-22) 338.83.38

## P ENT COOPERATION TREA

PCT

## NOTIFICATION OF ELECTION

(PCT Rule 61.2)

From the INTERNATIONAL BUREAU

To:

Assistant Commissioner for Patents  
United States Patent and Trademark  
Office  
Box PCT  
Washington, D.C.20231  
ETATS-UNIS D'AMERIQUE

in its capacity as elected Office

<b>Date of mailing (day/month/year)</b> 02 June 2000 (02.06.00)	
<b>International application No.</b> PCT/BE99/00128	<b>Applicant's or agent's file reference</b> DPPC 126.595
<b>International filing date (day/month/year)</b> 15 October 1999 (15.10.99)	<b>Priority date (day/month/year)</b> 21 October 1998 (21.10.98)
<b>Applicant</b> DE WINTER, Hugo et al	

1. The designated Office is hereby notified of its election made:

☒ in the demand filed with the International Preliminary Examining Authority on:

10 May 2000 (10.05.00)

☐ in a notice effecting later election filed with the International Bureau on:2. The election ☒ was☐ was not

made before the expiration of 19 months from the priority date or, where Rule 32 applies, within the time limit under Rule 32.2(b).

The International Bureau of WIPO 34, chemin des Colombettes 1211 Geneva 20, Switzerland	<b>Authorized officer</b>  Juan Cruz
Facsimile No.: (41-22) 740.14.35	Telephone No.: (41-22) 338.83.38

## PATENT COOPERATION TREATY

PCT

RECD 27 JUL 2000

WIPO

PCT

## INTERNATIONAL PRELIMINARY EXAMINATION REPORT

(PCT Article 36 and Rule 70)

Applicant's or agent's file reference D126595/V505182	<b>FOR FURTHER ACTION</b> See Notification of Transmittal of International Preliminary Examination Report (Form PCT/IPEA/416)	
International application No. PCT/BE99/00128	International filing date (day/month/year) 15/10/1999	Priority date (day/month/year) 21/10/1998
International Patent Classification (IPC) or national classification and IPC B29C43/18		
Applicant RECTICEL et al.		

1. This international preliminary examination report has been prepared by this International Preliminary Examining Authority and is transmitted to the applicant according to Article 36.



2. This REPORT consists of a total of 5 sheets, including this cover sheet.

- ☐ This report is also accompanied by ANNEXES, i.e. sheets of the description, claims and/or drawings which have been amended and are the basis for this report and/or sheets containing rectifications made before this Authority (see Rule 70.16 and Section 607 of the Administrative Instructions under the PCT).

These annexes consist of a total of sheets.

3. This report contains indications relating to the following items:

- I ☒ Basis of the report
- II ☐ Priority
- III ☐ Non-establishment of opinion with regard to novelty, inventive step and industrial applicability
- IV ☐ Lack of unity of invention
- V ☒ Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement
- VI ☐ Certain documents cited
- VII ☒ Certain defects in the international application
- VIII ☒ Certain observations on the international application

Date of submission of the demand  10/05/2000	Date of completion of this report  24.07.2000
Name and mailing address of the international preliminary examining authority:  European Patent Office D-80298 Munich Tel. +49 89 2399 - 0 Tx: 523656 epmu d Fax: +49 89 2399 - 4465	Authorized officer  Golombek, G  Telephone No. +49 89 2399 2909 

**INTERNATIONAL PRELIMINARY  
EXAMINATION REPORT**

International application No. PCT/BE99/00128

**I. Basis of the report**

1. This report has been drawn on the basis of (*substitute sheets which have been furnished to the receiving Office in response to an invitation under Article 14 are referred to in this report as "originally filed" and are not annexed to the report since they do not contain amendments.*):

**Description, pages:**

1-20 as originally filed

**Claims, No.:**

1-20 as originally filed

**Drawings, sheets:**

1/6-6/6 as originally filed

2. The amendments have resulted in the cancellation of:

- ☐ the description, pages:  
☐ the claims, Nos.:  
☐ the drawings, sheets:

3. ☐ This report has been established as if (some of) the amendments had not been made, since they have been considered to go beyond the disclosure as filed (Rule 70.2(c)):

4. Additional observations, if necessary:

**INTERNATIONAL PRELIMINARY  
EXAMINATION REPORT**

International application No. PCT/BE99/00128

**V. Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement**

**1. Statement**

Novelty (N)	Yes:	Claims	1-20
	No:	Claims	
Inventive step (IS)	Yes:	Claims	1-20
	No:	Claims	
Industrial applicability (IA)	Yes:	Claims	1-20
	No:	Claims	

**2. Citations and explanations**

**see separate sheet**

**VII. Certain defects in the international application**

The following defects in the form or contents of the international application have been noted:

**see separate sheet**

**VIII. Certain observations on the international application**

The following observations on the clarity of the claims, description, and drawings or on the question whether the claims are fully supported by the description, are made:

**see separate sheet**

**To point V**

**Claim 1**

Document D1 = EP-A-0 711 658 discloses a method for manufacturing a multi-layered moulded synthetic part comprising at least a preformed elastomeric moulded skin and a moulded carrier of a thermoplastic material, the method comprises the steps of:

- a moulding the elastomeric skin,  
and
- b moulding the thermoplastic material for the carrier in molten state to the back of said moulded skin.

D1 and the other documents of the search report are quiet about that the skin should be made of a thermosetting synthetic material when combined with feature (b).

There is also no hint for a person skilled in the art for such a combination.

Thus, the subject-matter of claim 1 is new and industrially applicable and it involves an inventive step and the claim itself meets the requirements of Article 33 PCT.

**Claims 2 - 16**

These dependent claims disclose preferred embodiments of the method claimed.

**Claim 17**

Document D1 also discloses an article comprising at least a preformed elastomeric skin and a carrier of a thermoplastic material which is moulded in molten state to the back of the skin.

D1 and the other documents of the search report are quiet about that the skin should be made of a thermosetting synthetic material and at the same time the carrier should be moulded in a molten state directly on the back of the skin.

There is also no hint for a person skilled in the art for such a combination.

Thus, the subject-matter of claim 17 is new and industrially applicable and it involves an inventive step and the claim itself meets the requirements of Article 33 PCT.

**Claims 18 - 20**

These dependent claims disclose preferred embodiments of the product claimed.

**To point VII**

The features of the claims are not provided with reference signs placed in parentheses (Rule 6.2(b) PCT).

**To point VIII**

The feature (a) of claim 1 is not clear, because the expression "moulding" used as a verb is a transformation step for a skin material which after this operation gets moulded and preformed at not the before this operation. Since this interpretaion is readable on the feature (a), the claim does not meet the requirements of Article 6 PCT.

# PCT

## INTERNATIONAL SEARCH REPORT

(PCT Article 18 and Rules 43 and 44)

Applicant's or agent's file reference <b>DPPC 126.595</b>	<b>FOR FURTHER ACTION</b> see Notification of Transmittal of International Search Report (Form PCT/ISA/220) as well as, where applicable, item 5 below.	
International application No. <b>PCT/BE 99/ 00128</b>	International filing date (day/month/year) <b>15/10/1999</b>	(Earliest) Priority Date (day/month/year) <b>21/10/1998</b>
Applicant <b>RECTICEL et al.</b>		

This International Search Report has been prepared by this International Searching Authority and is transmitted to the applicant according to Article 18. A copy is being transmitted to the International Bureau.

This International Search Report consists of a total of 3 sheets.

☒ It is also accompanied by a copy of each prior art document cited in this report.

### 1. Basis of the report

a. With regard to the language, the international search was carried out on the basis of the international application in the language in which it was filed, unless otherwise indicated under this item.

☐ the international search was carried out on the basis of a translation of the international application furnished to this Authority (Rule 23.1(b)).

b. With regard to any nucleotide and/or amino acid sequence disclosed in the international application, the international search was carried out on the basis of the sequence listing:

☐ contained in the international application in written form.

☐ filed together with the international application in computer readable form.

☐ furnished subsequently to this Authority in written form.

☐ furnished subsequently to this Authority in computer readable form.

☐ the statement that the subsequently furnished written sequence listing does not go beyond the disclosure in the international application as filed has been furnished.

☐ the statement that the information recorded in computer readable form is identical to the written sequence listing has been furnished

2. ☐ Certain claims were found unsearchable (See Box I).

3. ☐ Unity of invention is lacking (see Box II).

### 4. With regard to the title,

☒ the text is approved as submitted by the applicant.

☐ the text has been established by this Authority to read as follows:

### 5. With regard to the abstract,

☒ the text is approved as submitted by the applicant.

☐ the text has been established, according to Rule 38.2(b), by this Authority as it appears in Box III. The applicant may, within one month from the date of mailing of this international search report, submit comments to this Authority.

### 6. The figure of the drawings to be published with the abstract is Figure No.

☒ as suggested by the applicant.

☐ because the applicant failed to suggest a figure.

☐ because this figure better characterizes the invention.

1  
☐ None of the figures.



# INTERNATIONAL SEARCH REPORT

International Application No.  
PCT/BE 99/00128

**A. CLASSIFICATION OF SUBJECT MATTER**  
IPC 7 B29C43/18 B29C37/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B29C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0 386 818 A (RECTICEL) 12 September 1990 (1990-09-12) page 3, line 25 - line 51; claims; figures	1-20
Y	EP 0 540 941 A (SUMITOMO CHEMICAL CO) 12 May 1993 (1993-05-12) column 11, line 1 -column 13, line 3; claims; figures	1-20
A	EP 0 662 493 A (SUMITOMO CHEMICAL CO) 12 July 1995 (1995-07-12) page 8, line 20 -page 9, line 47; claims; figures	1-20
A	WO 98 33634 A (ATOMA INT INC) 6 August 1998 (1998-08-06) the whole document	1-3,9-20
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"Z" document member of the same patent family

Date of the actual completion of the international search

16 February 2000

Date of mailing of the international search report

23/02/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3018

Authorized officer

Labeeuw, R

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/BE 99/00128

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 93 23237 A (PREZ EDDIE DU ;DEBAES BERNARD (BE); JOURQUIN LUCIEN (BE); RECTICEL) 25 November 1993 (1993-11-25) cited in the application the whole document	1-3, 9, 10, 16-20
A	US 3 487 134 A (BURR WARREN W) 30 December 1969 (1969-12-30) the whole document	1-3, 10, 11, 13, 17
A	EP 0 303 305 A (RECTICEL) 15 February 1989 (1989-02-15) cited in the application the whole document	

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/BE 99/00128

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0386818	A	12-09-1990	BE 1002899 A AT 111397 T AU 624478 B AU 5012690 A CA 2011375 A DE 69012378 D DE 69012378 T DK 386818 T ES 2063242 T JP 3027914 A JP 7002337 B KR 9607304 B PT 93326 A,B US 5116557 A	16-07-1991 15-09-1994 11-06-1992 06-09-1990 03-09-1990 20-10-1994 16-02-1995 06-02-1995 01-01-1995 06-02-1991 18-01-1995 30-05-1996 07-11-1990 26-05-1992
EP 0540941	A	12-05-1993	CA 2080801 A DE 69225769 D DE 69225769 T JP 5208467 A KR 9512787 B	24-04-1993 09-07-1998 01-10-1998 20-08-1993 21-10-1995
EP 0662493	A	12-07-1995	JP 7228720 A JP 7227929 A CA 2138453 A US 5663210 A US 5576080 A	29-08-1995 29-08-1995 21-06-1995 02-09-1997 19-11-1996
WO 9833634	A	06-08-1998	US 5885662 A AU 3456797 A EP 0963283 A US 6017617 A	23-03-1999 25-08-1998 15-12-1999 25-01-2000
WO 9323237	A	25-11-1993	BE 1005821 A AT 160971 T AU 675219 B AU 4054893 A BR 9306374 A CA 2134781 A CN 1082981 A CZ 9402823 A DE 69315693 D DE 69315693 T EP 0642411 A ES 2111158 T HU 71501 A JP 7508939 T MX 9302896 A NO 944403 A PL 172033 B US 5662996 A	08-02-1994 15-12-1997 30-01-1997 13-12-1993 01-09-1998 25-11-1993 02-03-1994 12-07-1995 22-01-1998 02-04-1998 15-03-1995 01-03-1998 28-12-1995 05-10-1995 28-02-1994 23-11-1994 31-07-1997 02-09-1997
US 3487134	A	30-12-1969	BE 661654 A FR 1435257 A GB 1108426 A GB 1108427 A LU 48268 A NL 6503925 A SE 328399 B	16-07-1965 24-06-1966   26-05-1965 27-09-1965 14-09-1970

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/BE 99/00128

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0303305 A	15-02-1989	BE 1000767 A	28-03-1989
		AT 81034 T	15-10-1992
		AU 611450 B	13-06-1991
		AU 1853888 A	19-01-1989
		CA 1302801 A	09-06-1992
		CN 1030536 A,B	25-01-1989
		DE 3875029 A	05-11-1992
		DK 386488 A	17-01-1989
		FI 883246 A,B,	17-01-1989
		GR 3006184 T	21-06-1993
		IE 64847 B	06-09-1995
		JP 1094961 A	13-04-1989
		JP 2610308 B	14-05-1997
		KR 9613920 B	10-10-1996
		LV 10591 A	20-04-1995
		LV 10591 B	20-12-1995
		MX 171507 B	03-11-1993
		NO 302511 B	16-03-1998
		PH 26983 A	28-12-1992
		PL 273759 A	03-04-1989
		PT 87999 A,B	30-06-1989
		RU 2040346 C	25-07-1995
		US 5071683 A	10-12-1991


## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>7</sup> : B29C 43/18, 37/00	A1	(11) International Publication Number: WO 00/23239 (43) International Publication Date: 27 April 2000 (27.04.00)
(21) International Application Number: PCT/BE99/00128 (22) International Filing Date: 15 October 1999 (15.10.99) (30) Priority Data: 98870221.3                      21 October 1998 (21.10.98)                      EP (71) Applicants (for all designated States except US): RECTICEL [BE/BE]; Plejadenlaan 15, B-1200 Brussels (BE). LINPAC MOULDINGS LTD. [GB/GB]; 3180 Park Square, Birmingham B37 7YN (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): DE WINTER, Hugo [BE/BE]; Recticel N.V., Damstraat 2, B-9230 Wetteren (BE). VANLUCHENE, Yvan [BE/BE]; Recticel N.V., Damstraat 2, B-9230 Wetteren (BE). DEMANDT, Hans [BE/BE]; Linpac Mouldings Overpelt N.V., Stuijzandstraat 41, B-3900 Overpelt (BE). DEBLIER, Ivo [BE/BE]; Linpac Mouldings Overpelt N.V., Stuijzandstraat 41, B-3900 Overpelt (BE). HACKWELL, Roger [GB/GB]; Linpac Automotive, Old Southend Road, Great Burstead, Billericay, Essex CM11 2PY (GB). (74) Agents: VAN REET, Joseph et al.; Gevers & Vander Haeghen, Rue de Livourne 7, B-1060 Brussels (BE).		(81) Designated States: AE, AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), DM, EE, EE (Utility model), ES, FI, FI (Utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>

(54) Title: METHOD FOR MANUFACTURING A MULTI-LAYERED MOULDED SYNTHETIC PART AND THUS OBTAINED PART

## (57) Abstract

The invention relates to a method for manufacturing a multi-layered moulded synthetic part comprising a preformed elastomeric moulded skin (5), a moulded carrier (8) of a thermoplastic material and optionally an intermediate foam layer (6). In this method, the elastomeric skin (5) is moulded in a first step and the thermoplastic material for the carrier (8) is subsequently moulded in molten state to the back of said moulded skin (5). According to the invention, the moulded skin is made of a thermosetting synthetic material. Compared to a thermoplastic skin, such a thermosetting skin is less subjected to visible defects, in particular in case it has been provided with a superficial texture such as a leather grain, when the thermoplastic carrier is moulded thereto. Moulding of the thermoplastic carrier can be done by an injection moulding, an injection pressure moulding or a low pressure moulding technique.



**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LJ	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

**"Method for manufacturing a multi-layered moulded synthetic part  
and thus obtained part".**

5           The present invention relates to a method for manufacturing a multi-layered moulded synthetic part comprising at least a preformed elastomeric moulded skin and a moulded carrier of a thermoplastic material, which method comprises the steps of moulding said preformed elastomeric moulded skin, and moulding the thermoplastic material for the carrier in molten state to the back of said moulded skin.

10           Such a method is disclosed for example in EP-A-0 711 658. In the known method a PVC skin is first of all prepared by powder slush moulding in a first mould. This mould, which still carries the skin material on its moulding surface, is then inserted in an injection compression mould wherein a thermoplastic polypropylene carrier is injected. In order  
15           to achieve a sufficient adhesion between the PVC skin layer and the PP carrier, an adhesive layer, which may be formed by a foam layer, is applied against the back of the PVC skin prior to injecting the PP carrier.

20           A drawback of the method disclosed in EP-A-0 711 658 is that, due to the pressure and heat of the injected molten thermoplastic material, the front surface of the skin may be deformed or more particularly, in case the skin shows a grained surface, for example a leather grain, the superficial texture of the skin may be damaged or even lost. In case a reaction injection-moulding (RIM) process is used for moulding the rigid carrier, as disclosed for example in EP-B-0 642 411,  
25           considerably less heat and pressure are applied to the skin layer so that

- 2 -

the afore-mentioned drawback does not arise. However, compared to the known thermoplastic carriers, a RIM moulded carrier, in particular a polyurethane carrier has to show a larger thickness in order to provide the required mechanical strength, is less suited to include design concepts for mechanical functions (clips, gear-wheels, etc.), and involves higher production costs.

In EP-A-0 711 658 the damaging effect of the injection moulding step to the superficial skin texture is avoided or reduced by transferring the skin together with the mould surface onto which it was produced to the injection mould. Such a technique imposes however limitations to the design of the synthetic parts and does in particular not allow to produce so-called undercuts. Indeed, undercuts require the use of slides in the mould in order that the moulded parts can be demoulded and thus cause visible parting lines on the outer side of a skin moulded against such a composite mould surface.

An object of the present invention is therefore to propose a new method for manufacturing multi-layered moulded synthetic parts which enables to reduce the damaging effect of the step of moulding the thermoplastic carrier to the back of the skin layer and which allows in particular to mould the skin layer in or against a first mould and to transfer it to another mould for moulding the thermoplastic carrier without damaging the superficial texture which is usually applied onto the visible side of the skin.

To this end, the method according to the invention is characterised in that said moulded skin is made of a thermosetting synthetic material, in particular a thermosetting polyurethane material.

It has been found that it is possible to mould a rigid thermoplastic carrier to the back of such thermosetting skin without damaging for example the leather grain texture which may have been



- 3 -

provided on the visible side thereof, even when the skin has previously been transferred into another mould.

In an advantageous embodiment of the method according to the invention, the thermoplastic material for the carrier is moulded to the back of the skin according to an injection pressure moulding process in a mould which is only partially closed before the thermoplastic material is injected therein in molten state and which is further closed during and/or after the injection of the thermoplastic material so that a pressure is exerted by the mould onto the molten thermoplastic material or according to a low pressure moulding process in a mould wherein, before closing it, the thermoplastic material is laid down in molten state and, after having applied this thermoplastic material, the mould is closed so that a pressure is exerted by the mould onto the molten thermoplastic material.

In these embodiments, less pressure and/or heat is applied to the skin so that it will be less subjected to deformations, degradation, visible defects, etc.

In a preferred embodiment of the invention, the skin is moulded against a first mould surface and is transferred from this mould surface to a mould surface of the mould wherein the thermoplastic carrier is moulded.

This embodiment enables to produce skins or synthetic parts having complex shapes since, due to its flexibility, the skin can be removed easily from a complex mould surface showing in particular undercuts and can subsequently be positioned in a similar complex mould showing, however, the necessary slides to enable demoulding of the produced rigid synthetic part. On the parting lines of the slides, visible lines can be avoided by injecting the thermoplastic material at a sufficient low temperature and by closing the mould without generating a too high pressure therein.

- 4 -

In the present embodiment a grained skin can either be produced on the first mould surface or on the mould surface of the mould to which the skin is transferred and wherein the thermoplastic carrier is moulded. In the latter case, it has indeed been found that it is possible to  
5 apply a pressure and temperature to the skin when moulding the thermoplastic carrier which are sufficiently high to achieve the required deformation of the visible side of the skin but which are nevertheless still below the limits above which degradation of the skin or visible defects occur. For achieving the required pressure and temperature, preference  
10 is then given to an injection moulding process wherein the thermoplastic material for the carrier is moulded to the back of the skin in an injection mould wherein the thermoplastic material is injected in molten state after the mould has been closed

In an alternative embodiment, the skin can also be  
15 moulded against a mould surface which is either already situated in the mould wherein the thermoplastic carrier is moulded or which is transferred thereto after having moulded the skin on this mould surface.

An important advantage of this embodiment is that the skin is automatically in an accurate position in the mould wherein the  
20 thermoplastic carrier is moulded since the skin remains perfectly positioned on the mould surface. A further important advantage is that the skin adheres somewhat to the mould surface, even in case a mould release agent has first been applied thereto, so that it will not be locally stretched or elongated in the mould for forming the carrier when the  
25 thermoplastic material is injected therein through several injection gates or in other words so that there is no risk that bubbles will be formed.

The present invention further also relates to a multi-layered moulded synthetic part which is made in particular by the method according to the invention and which comprises at least a preformed  
30 elastomeric moulded skin and a carrier of a thermoplastic material which

- 5 -

is moulded in molten state to the back of said skin layer. The synthetic part according to the invention is characterised in that the moulded skin is made of a thermosetting synthetic material, in particular a polyurethane material.

5 Further particularities and advantages of the method and the synthetic parts according to the invention will become apparent from the following description of some particular embodiments of the invention. This description is only given by way of example and is not intended to limit the scope of the invention. The reference numerals used hereinafter relate to  
10 the annexed drawings wherein :

Figure 1 shows a schematic representation of the different steps of a first embodiment of the method according to the invention ; and

Figures 2 to 7 show schematically the different steps of a second embodiment of the method according to the invention.

15 In these different figures, the same reference numerals relate to the same or to analogous elements.

The invention generally relates to a method for manufacturing a multi-layered moulded synthetic part comprising at least a preformed elastomeric moulded skin and a moulded carrier of a thermoplastic material. Such multi-layered synthetic parts, in particular self-supporting trim parts are especially used as car interior parts such as dashboards, door panels, consoles, glove compartments, etc.

20 In the method according to the invention the preformed moulded skin is applied in a mould, the thermoplastic material for the carrier is applied in molten state to the back of the skin in the mould and is allowed to harden, and the obtained part is removed from the mould.

25 Applying the preformed moulded skin in the mould for moulding the thermoplastic carrier can be done in two ways. First of all it is possible to mould the skin against a mould surface which is either situated  
30 already in the mould for moulding the carrier or which is transferred thereto

- 6 -

together with the skin moulded thereon (see Figure 1). On the other hand, the skin can be moulded against a first mould surface and subsequently transferred from this first mould surface onto a mould surface of the mould for making the carrier (see Figures 2-4).

5                   When moulding the thermoplastic carrier in molten state in the mould, the skin layer is subjected to an amount of heat and pressure. In order to avoid or reduce visible defects to the skin as a result of this heat and pressure, use is made in the method according to the invention of a skin made of a thermosetting material, in particular a polyurethane material.

10                   By the expression "thermosetting material" is meant a material which, in contrast to a thermoplastic material, cannot be molten to such an extent that it is possible to pour or inject it in molten state in a mould to make a moulded part thereof. However, it does not mean that it cannot be molten to an extent which is sufficient to alter the superficial texture of a part  
15                   made thereof. In general, when moulding the intended "thermosetting materials" they require further chemical reactions or curing to solidify.

                  For moulding the thermosetting, in particular elastomeric polyurethane skins, different techniques can be used. The skin may for example be made by a RIM (reaction injection moulding) process. In this  
20                   process, two or more reaction components, especially a polyol and a isocyanate component are injected in a closed mould, and the reaction mixture is allowed to cure to produce the polyurethane skin. On the other hand, the skin can also be moulded against a mould surface by a spray technique, for example by the technique described in EP-B-0 303 305.  
25                   Suitable reaction mixtures for making the skin by the RIM or spray process are disclosed for example in EP-B-0 379 246. The reaction mixtures disclosed herein are light-stable PU reaction mixtures based on aliphatic polyisocyanates. Although preference is given to such aliphatic polyisocyanates, it is however also possible to use aromatic isocyanates for  
30                   producing the skin. In this case, the skin is preferably covered with a paint to

- 7 -

protect it against the light. Further, the thermosetting skin can also be made according to a powder or liquid slush moulding process wherein the mould surface is heated so that a final reaction or curing of the material is obtained. All of the above moulding processes offer the advantage that small design  
5 radii are possible namely as low as 0.5 mm in case of a leather grain or even sharp edges in case the skin shows no superficial texture whilst for the usual thermoformed skins, a curvature radius of 2 mm is already a problem.

The thermoplastic rigid carrier can be made of the various existing thermoplastic materials which are suited for providing a rigid support  
10 including especially polypropylene (PP), polycarbonate (PC), acrylnitril-butadiene-styrol (ABS), ABS blends, acrylester-styrol-acrylnitril (ASA), polystyrol (PS), thermoplastic polyurethane (TPU) or mixtures thereof or mixtures of any of these components with still other thermoplastic materials. According to the present invention, preference is given to PC, ABS and ABS  
15 blends and especially to ABS and ABS blends, in particular PC/ABS and ABS/PA (polyamide). For ABS and ABS blends, it has indeed been found that a good adhesion is directly obtained between the PU skin and the carrier without having to use any primer, glue, adhesion, etc. However, also when the carrier is made for example of PP, the necessary adhesion can be  
20 obtained by using an appropriate primer or an adhesive layer applied between the skin and the carrier. Such adhesive layers are for example disclosed in EP-A-0 711 658, the composition of which is incorporated herein by way of reference. In addition to a chemical adhesion, it is further especially also possible to obtain a mechanical anchoring. It is for example  
25 possible to apply a foam backing layer against the back of the skin before moulding the thermoplastic carrier. In this way, the molten material of the carrier can partially penetrate in the foam layer so that a mechanical anchoring effect is obtained.

Another way which may be considered for enhancing the  
30 adhesion between the skin and the carrier consists in admixing small

- 8 -

particles or fibres of the thermoplastic carrier material into the reaction mixture for making the skin. A number of these particles or fibres will be situated on the interface between skin and carrier and may thus provide the necessary adherence between these two layers. The particles incorporated  
5 in the skin have for example a diameter of 5 to 1500  $\mu\text{m}$  and in particular of 20 to 300  $\mu\text{m}$  whilst the fibres have for example a length of at least 4 mm and preferably a length of 12 to 100 mm.

This technique may especially be suited for adhering a PP carrier, or a thermoplastic intermediate foam layer, to a PU skin.

10 Hereafter, the technique for manufacturing the multi-layered synthetic part will be described more into detail with reference to the figures.

Figure 1 shows schematically a first embodiment of the method according to the invention.

On the mould surface 1 of a first mould part 2, which is  
15 arranged horizontally, there is applied, by spraying by means of a spray gun 4, a polyurethane elastomeric layer 5 which forms the skin 5 of the synthetic part. As mentioned already hereabove, this can be done according to the technique described in European patent No. 0 303 305 of one of the present applicants.

20 In a second step, a reaction mixture for obtaining a polyurethane foam layer 6 is sprayed by means of a second spray gun 7 against the back of the polyurethane skin 5, preferably when the skin 5 is still somewhat sticky.

Then, in a third step, the mould part 2 is transferred to an  
25 injection pressure mould wherein the mould part 2 is arranged substantially vertically and wherein it cooperates with a second mould part 3 to form the mould cavity. The mould 2, 3 is partially closed and a suitable thermoplastic material for obtaining the rigid synthetic carrier 8 is injected under pressure into the mould cavity through one or more injection gates 9. Subsequently,

- 9 -

the mould 2, 3 is entirely closed in order to divide the thermoplastic material homogeneously over the entire mould cavity.

For producing the polyurethane skin 5 a light-stable, mass-stained coloured polyurethane reaction mixture is sprayed in the first embodiment, as shown in figure 1, against the mould surface 1. Such reaction mixtures are for example disclosed in European patent No. 0 379 246 of one of the present applicants. These light-stable reaction mixtures are based on an aliphatic polyisocyanate. It is also possible to use reaction mixtures based on aromatic isocyanates, preference being however given to aliphatic isocyanates in view of the higher (light) stability thereof.

In a variant embodiment, a light-stable coloured polyurethane paint or in other words a so-called PU in mold paint, is applied first, in the first step, onto the mould surface. This paint composes together with the elastomeric layer subsequently applied thereto, the polyurethane skin 5. In this embodiment, use can be made without problems of an aromatic polyurethane system for the elastomeric layer since the elastomeric skin is in this way protected from the light.

The polyurethane skins are usually manufactured against a mould surface, the surface structure of which is provided with a superficial texture for giving the skins in particular the look of natural leather. The polyurethane foam 6 which is applied against the back of these skins 5, and which is preferably an open cell foam, provides for a so-called soft touch. The reaction mixture for obtaining the polyurethane foam layer 6 is preferably composed in such a manner that a semi-flexible polyurethane foam is obtained. Especially the amount of so-called cross-linkers in the reaction mixture is important in this respect. In a particular embodiment, use is made in this reaction mixture substantially exclusively of water as blowing agent. The polyisocyanate component is for example based on MDI.

In a preferred embodiment, an open-cell polyurethane foam layer 6 having a thickness of 0.1 to 30 mm and preferably of 2 to 3 mm is

- 10 -

applied. In order to approach as much as possible the touch of natural leather, such a foam layer 6 is combined with a polyurethane skin 5 having a thickness of 0.1 to 10 mm and preferably of 0.5 to 1.5 mm. Instead of applying a real foam backing layer 6, this layer could also be made of an elastomeric layer which is softer than the outer elastomeric skin layer in order to produce the desired soft-touch effect. The backing layer could alternatively also be prepared in advance and glued or otherwise adhered to the back of the skin layer. Also other techniques, such as for example RIM techniques or even liquid or powder slush moulding techniques could be employed for providing the soft or foam backing layer against the thermosetting skin layer. In contrast to the outer skin layer, these backing layers can, according to the invention, be made of a thermoplastic material. This offers the advantage that the thermoplastic carrier may show a stronger adherence to such thermoplastic backing layers than for example to a PU layer, especially in case the carrier is made of PP or another polyolefin.

In order to finish the trim part further on the back or inner side, a skin layer may also be applied against the mould surface 10 of the second mould part 3 in the first step.

In a first embodiment, a polyurethane paint is sprayed against the mould surface 10, either or not followed by the application of an elastomeric skin layer and a further polyurethane foam layer. In the latter case, a leather like coating is also obtained on the back.

Instead of the combination of the polyurethane paint layer and the elastomeric layer, it is of course also possible to use an elastomeric skin layer as such, in particular a light-stable polyurethane skin layer.

For moulding the thermoplastic carrier at the back of the skin, different moulding techniques can be used.

As mentioned already hereabove, the thermoplastic material for the carrier can be injected in the mould 2,3 when this mould is only partially closed. The mould 2,3 is then further closed when the thermoplastic



- 11 -

material is being injected in the mould and/or when it has already been injected. In this embodiment, the carrier is in other words produced according to a so-called injection pressure moulding process. When injecting the thermoplastic material the mould parts may be separated in particular about 1 to 30 mm ("Hinterprägen") or even completely open ("Hinterpressen").

In the method according to the invention, the mould parts are preferably separated less than 10 mm when injecting the thermoplastic material. An important advantage of this technique is that the large pressure at which the molten material is injected does not act directly onto the skin material but is considerably reduced due the fact that this pressure can escape laterally in the mould cavity.

It has been found that, in this way, the injection pressure has no or nearly no influence on the skin properties but that especially the pressure exerted when closing the mould 2,3 may be important and also the time period within which the mould is closed. The pressure exerted on the molten thermoplastic material is more particularly preferably situated between 1 and 350 kg/cm<sup>2</sup> and more preferably between 10 and 80 kg/cm<sup>2</sup> whilst the mould is preferably closed within a closing time shorter than 15 seconds and most preferably within 2 to 6 seconds. In the first phase after having injected the thermoplastic material, the mould is preferably closed as quickly as possible since, in a second phase, the other material becomes already more viscous so that the mould has to be closed slower to avoid too high pressures in the mould. In order to maintain the pressure within the above limits, the force at which the mould is closed can be controlled. Further, the pressure can be reduced by making thicker carriers and by using more injection gates so that less pressure has to be exerted for distributing the molten material over the skin layer when closing the mould. Finally, the chemical composition of the thermoplastic material can be chosen in order to reduce the viscosity of the molten material and in this way

- 12 -

thus also the pressure required for distributing this material over the skin layer.

Another technique which can be used is the so-called low pressure moulding technique. In a low pressure moulding process, the molten thermoplastic material is laid down or deposited in the pressure mould in the form of a slice when this mould is still open. In contrast to the injection pressure moulding technique or the injection moulding technique set forth hereafter, the mould is preferably arranged with the one mould half situated on top of the other so that the mould is opened or closed according to a substantially vertical movement. The thermoplastic material can either be laid down onto the back of the skin layer or onto the opposite mould part. This latter embodiment offers the advantage that the thermal effects on the skin are smaller. The thermoplastic material is preferably laid down onto the lower mould half whilst the skin is arranged against the surface of the upper mould half. After having laid down the thermoplastic material, the mould is closed so that a pressure is exerted on the molten thermoplastic material in order to spread it over the back of the skin. In this embodiment also, the same preferred pressures and closing times as set forth hereabove for the injection pressure moulding technique are applicable as well as the different measures for reducing the pressure required for distributing the molten thermoplastic material over the skin layer. In this embodiment, an increased number of injection gates corresponds of course to a better initial spreading of the molten material, i.e. by using thinner slices, when depositing a bead of this material in the mould.

A third technique which can be used for moulding the thermoplastic carrier is the so-called injection moulding technique. In this technique the thermoplastic material is injected in molten state in an injection mould after having closed this mould. In this embodiment higher pressures and temperatures are exerted on the skin layer but it has been observed that even in this case these pressures and temperatures can be

- 13 -

kept below the limits at which skin degradation may occur. In case the skin is not transferred to another mould surface, there is further also no or nearly no detrimental effect on any superficial texture of the skin layer.

5                   However, in some cases, in particular in case of parts showing undercuts, it may appear to be necessary to make the skin in one mould and to transfer it to another mould for making the thermoplastic carrier. In case a grained skin is to be made, preference is given with the first two techniques, i.e. with the injection pressure moulding technique and the low pressure moulding technique, to a process wherein the grain texture is provided in the  
10                   mould surface against which the skin is moulded, the mould surface of the mould wherein the carrier is moulded being then preferably free of any superficial texture. In this way, no signs of an additional grain structure can be formed on the skin surface.

                  In an injection moulding process, the original skin texture may  
15                   however quite easily be damaged in the injection mould. In this case, the skin is preferably first produced without any superficial textures. If desired, a superficial texture is then obtained in the mould wherein the carrier is injection moulded by providing the injection mould with the necessary texture. It has been found that, notwithstanding the fact that the skin is made  
20                   of a thermosetting material, the texture on the mould surface can be transferred to the skin by applying sufficient heat and pressure thereto. An injection moulding process is especially suited herefor. In case the injected molten material would exert locally a too high pressure onto the skin layer, it is also in this embodiment possible to use several injection gates.  
25                   Moreover, in this embodiment it appeared to be advantageous to inject the thermoplastic material through injection gates situated in the mould part against which the skin layer is positioned. In this way, the thermoplastic material is injected against the opposite mould part and thus not directly against the skin layer.

- 14 -

The parts produced in accordance with the method according to the present invention can easily be recognised from the parts which are actually on the market and which consist of a moulded PU skin and a moulded carrier which are fixed to one another by moulding a PU foam layer between the skin and the carrier. Indeed, due to the fact that the thermoplastic carrier is moulded either directly against the elastomeric skin layer or against an intermediate foam layer, it shows a much coarser surface on its side directed towards the skin compared to its back which is moulded against the mould surface.

#### Example 1

The method according to this example is in particular suited for manufacturing a door trim having a surface of for example 10 dm<sup>2</sup>. The model of this door trim included no undercuts so that only one two-part mould, analogous to the one indicated in figure 1, had to be used for the whole process. The mould part 2 of this mould comprised a galvanoplate showing a leather structure.

In a preparatory step, the mould part 2 was treated with a mould release agent such as for example Acmosil 180 SFC (Acmos) or Aquathan 61-360 (Block Chemie).

On the mould part 2 a polyurethane skin 5 was produced by means of a two-component spray gun 4. For manufacturing this skin 5 use was made of the Colofast<sup>®</sup> Spray system (trademark of Recticel) which allowed to produce a mass-stained light-stable microcellular elastomeric skin. The first component of this system, i.e. Isofast 3430 A (Recticel), was supplied at a flow rate of 3.67 g/sec, whereas the second component, i.e. Polyfast 3530 A (Recticel), was supplied at a flow rate of 6.33 g/sec. The total flow rate comprised therefore 10.0 g/sec. The controlled spray time comprised 10 sec. In this way a polyurethane skin 5 was obtained having a thickness of about 1 mm.

- 15 -

Immediately after the reaction, a layer of about 2 mm semi-flexible open-cell polyurethane foam 6 was applied on top of this polyurethane skin 5 by means of a second two-component spray gun 7. For producing this foam layer 6 use was made of the following waterblown MDI system :

Polyol component :

	Specflex NM 805 (Dow)	100
	Butanediol 1,4 (Hüls)	3
	Water 0.9	
10	Dabco 33Lv (Air Products)	1.0
	Fomrez UL28 (Witco)	<u>0.05</u>
	Total	104.95

Isocyanate component : Suprasec VM12 (I.C.I.) 24.12

Isocyanate index : 60

15 Flow rate of polyol component : 4.88 g/sec

Flow rate of isocyanate component : 1.12 g/sec

Total flow rate : 6.00 g/sec.

After a controlled spray time of 10 sec. with the spray gun 7, a thin layer of semi-flexible open-cell foam provided with a natural skin  
20 towards the side of the gun was obtained having a total thickness of  $\pm 2$  mm and the so-called overall density of which comprised  $\pm 450$  gr/litre.

By adjusting the robot program the thickness of the semi-flexible layer may vary from place to place. This thin foam layer gives the elastomeric "Colofast" skin, a so-called soft touch specific to natural leather.

25 After having produced the skin 5 and foam layer 6 onto the mould part 2, this mould part 2 was transferred to an injection pressure mould wherein it cooperated with a second mould part 3 to form the mould cavity for producing the rigid carrier 8. Before injecting the thermoplastic material for the carrier 8, the mould 2,3 was partially closed so that an  
30 opening of 8 mm remained between both mould halves 2,3. An ABS/PC blend was then injected through four injection gates 9 into the mould 2,3. This ABS/PC blend consisted of Bayblend T64 (Bayer) and was heated to a

- 16 -

temperature of 260°C whilst the mould was heated to a temperature of 30°C. The ABS/PC blend was injected within an injection time of 4 seconds and entered the mould cavity at a pressure of about 70 to 90 bars. After having injected the thermoplastic material, the mould 2, 3 was immediately closed, at a constant speed, within a closing time of 2 seconds. Subsequently, a back pressure of 10 bars was maintained for 5 seconds after which the pressure was removed. After a cooling time of 35 seconds, the produced part was demoulded. The so-obtained multi-layered moulded part had an average thickness of about 6 mm. No visible defects were caused by the injection pressure moulding step to the outer surface of the skin layer 5. The adherence of the skin and foam layer to the rigid carrier was good without having to use any adhesive or primer.

#### Example 2

This example is identical to Example 1 except for the fact that the "Colofast" polyurethane skin was replaced by a so-called polyurethane inmold paint followed by a two-component aromatic microcellular elastomeric system.

The inmold paint was in this case a light-stable two-component PU system, in particular Isothan-IMP-2K-Klarlack ME 170 of ISL Chemie.

Some inmold paints such as for example Rimbond 200 of Mc. Pherson Industrial Coatings have self release properties, so that the amount of a mould release agent on the mould part 2 could be reduced or avoided. The thickness of the inmold paint film comprised  $\pm 20 \mu$ .

After evaporation of the solvent, which took about 30 sec., the second layer, a PU elastomer, was applied by means of a two-component gun. This solventless elastomeric system consisted of :

#### 1. Polyol-component

Polyethertriol : condensate of propylene en ethylene oxyde on glycerine - IOH index 28 - content of primary

- 17 -

	OH groups 85 %	90
	Dabco 33 Lv (Air Products)	2.25
	Butanediol (Hüls)	7.9
	Color paste	<u>5</u>
		105.15
5	Viscosity at 25°C in mPa.s	1060
	Viscosity at 45°C in mPa.s	320
	<u>2. ISO-component</u>	
	Isocyanate RMA 200 (Dow)	43.5
	Viscosity at 25°C in mPa.s	620
10	Viscosity at 45°C in mPa.s	126

This system was based on aromatic isocyanates and was therefore not light-stable or coloured. These lacking properties were obtained by the previously applied PU in mold paint. In this way, there was also obtained a light-stable coloured 100% PU skin. Also in this case, no visible defects were caused by the injection pressure step to the visible side of the skin.

### Example 3

Example 1 was repeated without spraying the foam layer 6 against the back of the skin layer 5. Use was further made of Stapron CM404 (DSM) as thermoplastic material for the carrier 8. This material was injected at 270°C at an injection pressure, at the entry of the mould cavity, of about 80 bar. The further parameters were identical to Example 1. The total moulding cycle comprised 55 seconds. Also in this example, a multi-layered part was produced which showed no visible defects on the visible side of the skin layer and wherein the skin layer adhered strongly to the carrier without having to use any adhesive or primer.

### Example 4

- 18 -

In the example a door trim part was manufactured consisting of a polyurethane skin 5, a semi-rigid polyurethane foam layer 6 and a rigid carrier 8. The different steps are shown in Figures 2 to 7.

5 In the first step, illustrated in Figure 2, a polyurethane skin 5 (of about 1 mm) was made in the same way and by means of the same materials as in example 1 by spraying with a spray gun 4 against one part 11 of a mould 11, 12. This mould part 11 was provided with a leather texture. In a second step, a semi-rigid foam was applied in the open mould 11, 12 on the back of the skin 5 (see Figure 3) by means of a two  
10 component mixing head (not shown) and the mould 11, 12 was closed to produce the foam layer 6 having a thickness of about 4 mm. (see Figure 4). The foam was a polyurethane foam made from 100 parts of Bayfill VP PU 0811D (Bayer) as polyol component and 36 parts of Desmodur 44 V20LF (Bayer) as isocyanate component. These components had a temperature of  
15 25°C and were passed through the mixing head at a total flow rate of 150 g/sec. The curing time of the foam comprised 250 seconds.

In a third step, illustrated in Figure 5, the laminate of the PU skin 5 and PU foam layer 6 was transferred into a low pressure mould 2, 3, and was more particularly positioned against the upper mould part 2 thereof.  
20 This upper mould part 2 was provided with the necessary slides 13 to enable undercuts in the moulded part. For accurately positioning the skin against the mould part 2, this mould part 2 was provided with vacuum channels 14 connected to a source of vacuum. Further, a clamping frame 15 was provided consisting of rods 16 fixed to the mould part 2 and of the  
25 actual frame 17 which was slideably mounted on the rods 16 and which carried clamps 18. These clamps 18 were used to clamp an edge portion 19 of the laminate 5, 6, which was not provided with a foam backing 6, against the upper mould part 2 as shown in Figure 6.

In a fourth step, also illustrated in Figure 6, a slice 20 of  
30 ABS/PC (Bayblend T44 of Bayer) was laid down onto the lower mould part 3



- 19 -

and, in a fifth step, the mould 2,3 was closed (see Figure 7). In this fifth step, the slice of thermoplastic material was homogeneously spread in the mould cavity by the pressure exerted thereon. The thermoplastic ABS/PC material was laid down at a temperature of 260°C in a slice having a width of 10 cm.

5 Closing of the press was done in three steps:

- at full speed until the mould parts 2, 3 were 8 mm apart;
- at 10 mm/sec when closing the mould from 8 to 7 mm opening and
- at 3 mm/sec when closing the mould further from 7 to 0 mm opening.

10 After having closed the mould completely, the following successive back pressures were maintained:

- 70 tons during 2 sec
- 50 tons during 3 sec
- 30 tons during 5 sec.

15 During the subsequent cooling phase of 50 seconds, no additional pressure was exerted onto the mould.

The multi-layered moulded part produced in this example had a total surface of about 14 dm<sup>2</sup>. The leather texture on the outer side of the skin layer showed no visual defects and there was a good adherence  
20 between the different layers.

#### Example 5

Example 4 was repeated without providing a foam layer 6 between the back of the skin 5 and the rigid carrier 8. In this example also, the leather texture on the outer side of the skin layer showed no visible  
25 defects notwithstanding the fact that this skin layer was not shielded off from the injected thermoplastic material by an insulating foam layer and notwithstanding the fact that the skin layer was transferred to a pressure mould which showed no superficial texture. Moreover, there was obtained a strong adhesion between the polyurethane skin layer and the ABS/PC  
30 thermoplastic synthetic carrier.

- 20 -

From the above description, it will be clear that the invention is in no way limited to the hereabove described embodiments but that many modifications can be considered within the scope of the invention as defined in the appended claims. In particular, one could consider admixing some  
5 other materials into the different layers such as for example reinforcing fibers or adding additional reinforcing layers, especially a glass fiber mat between the skin layer and the rigid carrier.

- 21 -

CLAIMS

1. A method for manufacturing a multi-layered moulded synthetic part comprising at least a preformed elastomeric moulded skin and a moulded carrier of a thermoplastic material, which method  
5 comprises the steps of:

- (a) moulding said preformed elastomeric moulded skin, and
- (b) moulding the thermoplastic material for the carrier in molten state to the back of said moulded skin,

characterized in that said moulded skin is made of a thermosetting synthetic material.  
10

2. A method according to the previous claim, characterized in that said thermosetting material is a polyurethane material.

3. A method according to claim 1 or 2, characterized in that said preformed skin is made by a spray, a RIM or a slush moulding process.  
15

4. A method according to any one of the previous claims, characterized in that the thermoplastic material for the carrier is moulded to the back of the skin according to an injection pressure moulding process in a mould which is only partially closed before the thermoplastic material is injected therein in molten state and which is further closed during and/or after the injection of the thermoplastic material so that a pressure is exerted by the mould onto the molten thermoplastic material.  
20

5. A method according to any one of the claims 1 to 3, characterized in that the thermoplastic material for the carrier is moulded to the back of the skin according to a low pressure moulding process in a mould wherein, before closing it, the thermoplastic material is laid down in molten state in the mould and, after having applied this thermoplastic material, the mould is closed so that a pressure is exerted by the mould onto the molten thermoplastic material.  
25

- 22 -

5 6. A method according to claim 4 or 5, characterized in that after having applied the thermoplastic material in said mould, this mould is closed in such a manner that the pressure exerted by the mould on the molten thermoplastic material is situated between 1 and 350 kg/cm<sup>2</sup> and preferably between 10 and 80 kg/cm<sup>2</sup>.

7. A method according to any one of the claims 4 to 6, characterized in that said mould is closed within a closing time shorter than 15 seconds, preferably within 2 to 6 seconds.

10 8. A method according to any one of the claims 1 to 3, characterized in that the thermoplastic material for the carrier is moulded to the back of the skin according to an injection moulding process in a mould wherein the thermoplastic material is injected in molten state after the mould has been closed.

15 9. A method according to any one of the previous claims, characterized in that, before moulding the thermoplastic material for the carrier to the back of the skin, a softer layer, in particular a foam backing layer, is applied against the back of the skin, which softer layer is preferably made of a polyurethane material.

20 10. A method according to the previous claim, characterized in that said foam backing layer is sprayed against the skin or is applied thereto in a mould according to a RIM process.

25 11. A method according to any one of the previous claims, characterized in that said skin is moulded against a mould surface which is either situated in the mould wherein the thermoplastic carrier is moulded or which is transferred thereto after having moulded the skin on this mould surface.

30 12. A method according to any one of the claims 1 to 10, characterized in that said skin is moulded against a first mould surface and is transferred from this first mould surface to a mould surface of the mould wherein the thermoplastic carrier is moulded.

- 23 -

13. A method according to the previous claim, characterized in that said first mould surface shows a superficial texture in order to produce a grained skin.

5 14. A method according to the previous claim, characterized in that the mould surface of the mould to which the moulded skin is transferred is free of any superficial texture.

10 15. A method according to claim 12, characterized in that the mould surface of the mould to which the moulded skin is transferred shows a superficial texture which is, as a result of the pressure and heat applied to the skin during the moulding process of the thermoplastic carrier, transmitted thereto in order to produce a grained skin.

15 16. A method according to any one of the previous claims, characterized in that the thermoplastic material from which the carrier is made is selected from the group consisting of polypropylene (PP), polycarbonate (PC), acrylnitril-butadiene-styrol (ABS), ABS blends, in particular a PC/ABS or an ABS/PA blend, acrylester-styrol-acrylnitril (ASA), polystyrol (PS) and thermoplastic polyurethane (TPU), preferably from the group consisting of PC, ABS and ABS blends, and most preferably from the group consisting of ABS and ABS blends, in  
20 particular a PC/ABS or an ABS/PA blend.

25 17. A multi-layered moulded synthetic part comprising at least a preformed elastomeric moulded skin and a carrier of a thermoplastic material which is moulded in molten state to the back of said skin, characterized in that said moulded skin is made of a thermosetting synthetic material


18. A synthetic part according to the previous claim, characterized in that it comprises between the skin and the carrier a layer which is softer than the skin, in particular a foam backing layer, the carrier being moulded against the back of a laminate formed by the skin


- 24 -

and the softer layer, which softer layer is preferably made of a polyurethane material.

19. A synthetic part according to claim 17 or 18, characterized in that said thermosetting material is a polyurethane material.

5           20. A synthetic part according to any one of the claims 17 to 19, characterized in that said thermoplastic carrier shows a coarse surface on its side directed towards the skin.


**Fig. 1**




**Fig. 2**




3/6





**Fig. 3**



**Fig. 4**

*Fig. 5*

*Fig. 6*



## INTERNATIONAL SEARCH REPORT

Inventor and Application No.

PCT/BE 99/00128

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B29C43/18 B29C37/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B29C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0 386 818 A (RECTICEL) 12 September 1990 (1990-09-12) page 3, line 25 - line 51; claims; figures	1-20
Y	EP 0 540 941 A (SUMITOMO CHEMICAL CO) 12 May 1993 (1993-05-12) column 11, line 1 - column 13, line 3; claims; figures	1-20
A	EP 0 662 493 A (SUMITOMO CHEMICAL CO) 12 July 1995 (1995-07-12) page 8, line 20 - page 9, line 47; claims; figures	1-20
A	WO 98 33634 A (ATOMA INT INC) 6 August 1998 (1998-08-06) the whole document	1-3, 9-20
	-/-	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"G" document member of the same patent family

Date of the actual completion of the international search

16 February 2000

Date of mailing of the international search report

23/02/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+31-70) 340-3016

Authorized officer

Labeeuw, R

## INTERNATIONAL SEARCH REPORT

Int'l Application No.

PCT/BE 99/00128

## C. (Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 93 23237 A (PREZ EDDIE DU ;DEBAES BERNARD (BE); JOURQUIN LUCIEN (BE); RECTICEL) 25 November 1993 (1993-11-25) cited in the application the whole document	1-3, 9, 10, 16-20
A	US 3 487 134 A (BURR WARREN W) 30 December 1969 (1969-12-30) the whole document	1-3, 10, 11, 13, 17
A	EP 0 303 305 A (RECTICEL) 15 February 1989 (1989-02-15) cited in the application the whole document	

# INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/BE 99/00128

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0386818 A	12-09-1990	BE 1002899 A AT 111397 T AU 624478 B AU 5012690 A CA 2011375 A DE 69012378 D DE 69012378 T DK 386818 T ES 2063242 T JP 3027914 A JP 7002337 B KR 9607304 B PT 93326 A, B US 5116557 A	16-07-1991 15-09-1994 11-06-1992 06-09-1990 03-09-1990 20-10-1994 16-02-1995 06-02-1995 01-01-1995 06-02-1991 18-01-1995 30-05-1996 07-11-1990 26-05-1992
EP 0540941 A	12-05-1993	CA 2080801 A DE 69225769 D DE 69225769 T JP 5208467 A KR 9512787 B	24-04-1993 09-07-1998 01-10-1998 20-08-1993 21-10-1995
EP 0662493 A	12-07-1995	JP 7228720 A JP 7227929 A CA 2138453 A US 5663210 A US 5576080 A	29-08-1995 29-08-1995 21-06-1995 02-09-1997 19-11-1996
WO 9833634 A	06-08-1998	US 5885662 A AU 3456797 A EP 0963283 A US 6017617 A	23-03-1999 25-08-1998 15-12-1999 25-01-2000
WO 9323237 A	25-11-1993	BE 1005821 A AT 160971 T AU 675219 B AU 4054893 A BR 9306374 A CA 2134781 A CN 1082981 A CZ 9402823 A DE 69315693 D DE 69315693 T EP 0642411 A ES 2111158 T HU 71501 A JP 7508939 T MX 9302896 A NO 944403 A PL 172033 B US 5662996 A	08-02-1994 15-12-1997 30-01-1997 13-12-1993 01-09-1998 25-11-1993 02-03-1994 12-07-1995 22-01-1998 02-04-1998 15-03-1995 01-03-1998 28-12-1995 05-10-1995 28-02-1994 23-11-1994 31-07-1997 02-09-1997
US 3487134 A	30-12-1969	BE 661654 A FR 1435257 A GB 1108426 A GB 1108427 A LU 48268 A NL 6503925 A SE 328399 B	16-07-1965 24-06-1966   26-05-1965 27-09-1965 14-09-1970

# INTERNATIONAL SEARCH REPORT

information on patent family members

Int. and Application No.

PCT/BE 99/00128

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0303305 A	15-02-1989	BE 1000767 A	28-03-1989
		AT 81034 T	15-10-1992
		AU 611450 B	13-06-1991
		AU 1853888 A	19-01-1989
		CA 1302801 A	09-06-1992
		CN 1030536 A,B	25-01-1989
		DE 3875029 A	05-11-1992
		DK 386488 A	17-01-1989
		FI 883246 A,B,	17-01-1989
		GR 3006184 T	21-06-1993
		IE 64847 B	06-09-1995
		JP 1094961 A	13-04-1989
		JP 2610308 B	14-05-1997
		KR 9613920 B	10-10-1996
		LV 10591 A	20-04-1995
		LV 10591 B	20-12-1995
		MX 171507 B	03-11-1993
		NO 302511 B	16-03-1998
		PH 26983 A	28-12-1992
		PL 273759 A	03-04-1989
		PT 87999 A,B	30-06-1989
		RU 2040346 C	25-07-1995
		US 5071683 A	10-12-1991